

Munken Pure (US)

Extraordinary printing demands extraordinary design paper. The uncoated smooth surface of Munken Pure and its cream white shade convey distinct features to images and gives an exclusive very true authentic appeal. Munken Pure is developed for offset print and also suitable for various kinds of printing techniques; flexo, laser, xerography, digital printing, inkjet and for preprint applications. 80 & 90 g/m² / 54T & 61T lbs. are even further developed as a fully adapted preprint paper. Also available is a bright white, Munken Polar, a natural white version, Munken Lynx and the high white Munken Kristall.

Munken Pure standard products are available as EU Ecolabel, FSC® – The mark of responsible forestry. www.fsc.org. FSC-C020637 and PEFC™ PEFC/05-33-99 certified.



The mark of
responsible forestry



Technical specifications

Basic information:	Optimized for colour printing, Available in sheets, Available in reels
Surface:	Uncoated, Smooth
Shade:	Cream
Printing techniques:	Offset, Flexo, Laser, Inkjet (black/white)
Certificates/Statements:	FSC_C020637, PEFC_053399, EU Ecolabel, The paper is inspected for Nordic Ecolabelled printing , ECF, ISO 14001, EMAS, Paper Profile, Safety of Toys, Food contact, Age resistant (ISO 9706), Woodfree, Cradle to Cradle Certified®

Munken Pure

Grammage (g/m²)	80*	90*	100	120	130	150	170	200	240	300 ^B	400 ^B	600 ^B
-----------------------------------	-----	-----	-----	-----	-----	-----	-----	-----	-----	------------------	------------------	------------------

Basis Weight (Text 25x38) Lbs	54T	61T	67.5T	81T	88T	101.5T
--------------------------------------	-----	-----	-------	-----	-----	--------

Basis Weight (Cover 20x26) Lbs							63C	74C	89C	111C	148DTC	222DTC
---------------------------------------	--	--	--	--	--	--	-----	-----	-----	------	--------	--------

Opacity (%)	88	90	92	94	95	96	97	98	99	100	100	100
--------------------	----	----	----	----	----	----	----	----	----	-----	-----	-----

Caliper	4.1	4.6	4.5	5.3	5.8	6.7	7.6	8.9	10.7	13.3	17.8	26.7
----------------	-----	-----	-----	-----	-----	-----	-----	-----	------	------	------	------

Brightness (Tappi %)	81	81	81	81	81	81	81	81	81	81	81	81
-----------------------------	----	----	----	----	----	----	----	----	----	----	----	----

Smoothness (Tappi, Sheffield units)	120	120	120	120	120	120	120	120	120	120	120	120
--	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----	-----

^B Laminated paper

* Fully preprint adapted

Screen recommended 133-150 lpi

Values are targets only and can be subject to changes over time without prior notice. You will find the latest technical information and other technical recommendations about our products at arcticpaper.com